



DIMAL Asia Pacific Sdn. Bhd. (219956-D)

DIMAL MORTAR



High temperature and
refractory mortar

Innovating Mortar Solution

We Create Your Advantage

Dry Mortar Series

Grade	Appl. Temp. (°C)	Setting	Al ₂ O ₃	SiO ₂	CaO	Application
DIMOR D45	850 - 1600	Air Setting	39.0 min	54.0 max	-	Joint Mortar, coating
DIMOR D50	1500	Heat Setting	48.0 min	47.0 max	0.1	Joint Mortar, coating
DIMOR 70-D	1700	Air Setting	66.0 min	25.0 max	-	Joint Mortar, coating
DIMOR 70 MUL-D	1700	Air Setting	66.0 min	26.0 max	-	Joint Mortar, coating

Wet Mortar Series

Grade	Appl. Temp. (°C)	Setting	Al ₂ O ₃	SiO ₂	P ₂ O ₅ (Cr ₂ O ₃)	Application
DIMOR W45	1600	Air Setting	43.0 min	52.0 max	-	Joint Mortar, coating
DIMOR 50 MUL-S	1500	Air Setting	42.0	52.0	-	Joint Mortar, coating
DIMOR 160 MUL-S	1600	Air Setting	41.0 min	47.0 max	-	General purpose Joint Mortar
DIMOR 160 MUL-P	1600	Heat Setting	48.0 min	29.0 max	1.5	General purpose Joint Mortar
DIMOR 170 P	1600	Heat Setting	51.0 min	27.0 max	1.5	General purpose Joint Mortar
DIMOR 70 MUL S	1600	Air Setting	56.0 min	36.0 max	-	Joint Mortar, coating
DIMOR 70 MUL P	1700	Heat Setting	64.0 min	28.0 max	3.0	Joint Mortar, coating
DIMOR 180 P	1800	Heat Setting	91.0	4.0	3.0	Mortar for High Alumina and Silicon Carbide bricks
DIMOR 190 P	1900	Heat Setting	91.0	3.0	3.0	General purpose Joint Mortar
DIMOR 190 CR P	1900	Heat Setting	88.0	3.0	3.0 (3.5)	Joint Mortar for Slide Gate and Gas Purging Systems

This indicated values are average values. They should not be regarded as guaranteed specifications. We reserve the right to the editions of the technical product information arising from any new technical developments.

WE CREATE YOUR ADVANTAGE

DIMAL ASIA PACIFIC SDN. BHD. (219956-D)

3221 & 3226, Batu 29, Batang Kali, Selangor Darul Ehsan.

Tel : (603) 6075 2011 Fax : (603) 6075 2562

E-mail : office@dimal.com.my Website : www.dimal.com.my